

**DLW Linoleum LPX****chemical- and stain resistance** according to EN 423 / EN ISO 26987

<u>chemicals</u>	<u>Index after cleaning</u>	
	after 2 hours	after 30 minutes
ethanol (96%)	0	0
acetone (100%)	0	0
ethyl acetate (100%)	0	0
n-hexane (100%)	0	0
hydrogen peroxide (3%)	0	0
iodine solution (1%)	3	3
sulphuric acid (30%)	0	0
hydrochloric acid (10%)	0	0
nitric acid (10%)	0	0
sodium hydroxide (50%)	0	0
ammonia (25%)	1	0
white spirit	0	0
cleaning agent „Meister Proper“	0	0
abrasive cleaning agent „Viss“	1	0
acetic acid cleaning agent	0	0
basic cleaning agent „Linax GR“	1	1

Interpretation and presentation of results according to EN ISO 26987:

<u>Index</u>	<u>Effect of test after cleaning</u>
0	not affected
1	slightly affected
2	moderately affected
3	severely affected